

Green-Lock® Structural Adhesive



OVERVIEW & FEATURES

Green-Lock Structural Adhesive is a single component, hybrid polymer structural adhesive designed for difficult bonding and sealing applications. Green-Lock Structural Adhesive bonds tenaciously to asphalt and coal tar BUR, asphalt and coal tar modified bitumen, APP, many types of coated metal, metal flashing details, concrete, brickwork, lumber, many plastics, stone, aluminum, steel, ceramics, extruded polystyrene (XPS) insulation and glass.

VOC Compliant - Green-Lock Structural Adhesive is 100% solids, meaning it has very low odor and no shrinkage.

Strong & Flexible - Bonds tenaciously to metal, masonry or wood. Green-Lock Structural Adhesive (when cured) produces 300% elongation to accommodate the most severe amounts of building movement.

Low Temperature Flexibility - Green-Lock Structural Adhesive maintains its physical properties down to -40°F (-40°C).

No Slump - Green-Lock Structural Adhesive experiences no slump; it stays on the surface it is adhered to.

APPLICATION

Green-Lock Structural Adhesive is ready to use in its standard 10.1 fl. oz. (300 ml) cartridge. There is no settling or separation with Green-Lock Structural Adhesive. During cold weather, store product inside at room temperature to aid workability. Ensure all surfaces are clean and free from debris prior to application. All application surfaces need to be dry. Apply to either surface, then apply gentle pressure to form the bond. A recommended 3/8 in. (.95 cm) bead is recommended for applications.

Surface Preparation - Surfaces must be dry and free of all contaminants such as oil, grease, wax, dust, corrosion, loose aggregate, form-release agents.

Priming - Never use a substitute for proper surface preparation. Priming is not required on most common building materials. However, varieties of brick, natural stone, plastics, paints, coatings and other treatments of surfaces often present difficult substrates to which to adhere. Due to the number and unpredictable nature of these substrates, a field test

is recommended to determine the adhesion of Green-Lock Structural Adhesive. A field test to confirm this possibility is recommended.

Cleaning - Use alcohol or soap and water to remove excess sealant before it cures and to clean equipment. Cured Green-Lock Structural Adhesive can be removed by scraping or abrading.

Storage Life - Green-Lock Structural Adhesive has a warranted shelf life of 12 months from date of shipment from the factory when stored in original, unopened cartridges at conditions not exceeding 80°F (27°C), 50% R.H. Consistently higher temperatures and/or humidity will shorten this shelf life.

Tool Time (initial bond) - 1-2 hours at 77°F (25°C), 50% relative humidity. Higher temperatures and/or humidity will shorten this time.

PRECAUTIONS

- Avoid skin and eye contact
- Skin may be cleaned with mineral spirits and then washed thoroughly with soap and water
- May be harmful if swallowed; do not induce vomiting and call physician immediately
- Keep away from heat and flames
- Refer to Safety Data Sheet (SDS).

Green-Lock® Structural Adhesive

| Technical Data | Green-Lock Structural Adhesive |
|--|---|
| Hardness Shore A (ASTM C 661) | 53-59 ± 3 |
| Shear Strength (ASTM D 1002) | 120 psi |
| Tack-Free Time (ASTM C 679) | 17-20 minutes |
| Slump (sag) (ASTM C 697) | 0 slump |
| Shrinkage | No measurable shrinkage after 14 days |
| Low Temperature Flex. Pass ¼ in. mandrel | -20°F (-28.8°C) |
| Service Temperature | -40°F to 200°F (-40°C to 93°C) |
| Specific Gravity | 1.55 (12.95/gal) |
| Viscosity @ 70°F (20°C) Brookfield RVF, TF spindle, 2 RPM | 500,000 cP |
| Shelf Life | 1 year |
| Coverage Approximately 1/4 in. x 1/4 in. (.635 cm. x .635 cm) bead | 26 lineal feet (7.9 m) |
| Packaging | 10.1 oz. (300 ml) cartridge 24 cartridges per case |

| Eco-Facts | Green-Lock Structural Adhesive |
|-----------|--------------------------------|
| VOC | 0 g/l |

For specific recommendations and coverage rates, please contact your local Garland Representative or Garland Technical Service Department.



For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
209 Carrier Drive
Toronto, Ontario
Canada, M9W 5Y8
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

The Garland Company UK, LTD
Second Way Centre, Second Way
Avonmouth, Bristol UK BS11 8DF
Phone: 011 44 1174 401050 (Outside UK)
Toll Free: 0800 328 5560 (Only in UK)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. A ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or Garland Corporate Office for more information.

Garland Greenhouse and Green-Lock are trademarks of The Garland Company, Inc.