

# Cool-Sil™ FG

Flashing Grade Silicone Sealant



## OVERVIEW & FEATURES

Cool-Sil™ FG (flashing grade) is a 100% silicone, moisture-cure sealant that forms a tough, flexible and water-resistant membrane. It is ideal for sealing roof penetrations, drains, existing membrane seams and other flashing details on aged modified bitumen, single-ply membranes, built-up roof membranes and metal roofs.

**Low odor** - Cool-Sil FG has low VOC and low odor, making it suitable for a variety of applications.

**Easily applied** - This sealant can be applied simply by brush, trowel or putty knife. This, combined with the product's superior adhesion, ensures the sealant permeates those hard-to-reach places quickly and efficiently.

**Fast curing** - Despite its thick composition, Cool-Sil FG is tack-free within 1-2 hours. The product's moisture-curing composition speeds up the process toward full coverage.

## APPLICATION

The surface must be clean, dry and free from oils and other contaminants. Cool-Sil FG can be applied by brush, trowel, or putty knife. Coverage rates are theoretical and will vary based on surface texture and application conditions such as weather and slope. Cool-Sil FG is typically applied at 1/8 in. - 1/4 in. thickness depending upon the application and substrate.

**Weather Restrictions** - Cool-Sil FG silicone sealant should not be applied in ambient temperatures above 95°F. For cold weather applications, store material above 65°F before use.

**Typical Cure Rate** - At 77°F and 50% RH, the sealant is tack-free in 1-2 hours, with through cure (3/8" depth) being achieved between 12 and 18 hours.

Technical Data	Cool-Sil FG
<b>Color</b>	White
<b>Elongation</b> (ASTM D412)	275%
<b>Tensile Strength</b> (ASTM D412)	130 psi
<b>Solids Content</b> (ASTM 2697)	92% (+/-3)
<b>Tack-Free Time</b> (ASTM C679)	1-2 hrs
<b>Cure Time</b> (ASTM C679)	12-18 hrs
<b>VOC</b> (ASTM D396)	<50 g/L
<b>Shelf Life</b>	1 year, unopened and stored between 50°F and 90°F (10°C and 32°C)
<b>Packaging</b>	2 gal pail (7.6 L)

For more information, visit us at: [www.garlandco.com](http://www.garlandco.com)

**The Garland Company, Inc.**  
3800 East 91st Street  
Cleveland, OH 44105  
FAX: 216-641-0633  
Phone: 216-641-7500  
Toll Free: 800-321-9336

**Garland Canada Inc.**  
209 Carrier Drive  
Toronto, Ontario  
Canada, M9W 5Y8  
FAX: 416-747-1980  
Phone: 416-747-7995  
Toll Free: 800-387-5991  
(Only in Canada)

**The Garland Company UK, LTD**  
Second Way Centre, Second Way  
Avonmouth, Bristol UK BS11 8DF  
Phone: 011 44 1174 401050 (Outside UK)  
Toll Free: 0800 328 5560 (Only in UK)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or the home office for more information.

Cool-Sil is a registered trademark of The Garland Company, Inc.

© 2022 Garland Industries, Inc.