

OVERVIEW

FlexBase E 80 is an 80-mil, SBS rubber modified base sheet that utilizes a dual polyester and fiberglass combination reinforcement that offers the inherent strength and heat stability of fiberglass along with the ability of polyester to conform. The result is a high strength, puncture and fatigue resistant, rubber modified base sheet designed for application as the interply waterproofing and reinforcement layer of a modified or built-up roofing system. It provides long-term performance in all types of new or retrofit construction uses.

FlexBase E 80 can be used as the initial underlayment for any Garland HPR® roof system, used in conjunction with Weatherking® and Green-Lock® for a cold-applied system or used with hot asphalt or Garlastic® as a multi-ply BUR. It can also be used as a base flashing or interply in Garland's hot- or cold-applied systems.

Advanced Rubber Technology – The modifier utilized in FlexBase E 80 is SBS (Styrene-Butadiene-Styrene). When the SBS rubber is properly dispersed throughout the high penetration asphalt, the rubber provides increased thermal shock resistance, UV protection, heat resistance, elongation, and low temperature flexibility. To ensure proper dispersion, a special high shear mixer is used in manufacturing.

Superior Performance Characteristics – FlexBase E 80 exceeded the requirements of ASTM D 4601 by more than 50%. FlexBase E 80 imparts the strength and flexibility your roof requires to stand up to and overcome the elements.

Superior Strength – FlexBase E 80 is reinforced with one layer of fiberglass and one layer of polyester. The superior strength provided by the dual fiberglass and polyester combination resists the movement created by today's modern buildings. In addition, FlexBase E 80 provides tensile strength in excess of 500 pounds per inch (8929 kg/m) in the machine and cross machine direction. This translates to long-term resistance to splits and tears in the completed roof system.

APPLICATION

FlexBase E 80 can be used as the initial underlayment for any Garland HPR® roof system. Specifications for nailing to various decks are available. In addition, FlexBase E 80 is used as the underlayment in Garland's two (2) or three (3) ply hot asphalt or cold-applied Weatherking and Green-Lock systems and also can be used in three (3) or four (4) ply BUR's.

Note: All rolls must be cut in 18 ft. (5.5 m) lengths and allowed to relax prior to application.



Technical Data	FlexBase E 80
Tensile Strength	*MD 550 lbf./in. (96.25 kN/m) *XD 550 lbf./in. (96.25 kN/m) **MD 650 lbf./in. (114 kN/m) **XD 750 lbf./in. (132 kN/m)
*Tear Strength	MD 1,000 lbf. (4448 N) XD 1,000 lbf. (4448 N)
*Elongation	MD 9.0% XD 9.0%
*Low Temperature Flex	passes -40°F (-40°C)

Finished membrane meets and/or exceeds ASTM D 6162, TYPE III

Test Method ASTM D 5147 is tested at:

* 2 in./min. @ 73.4 ± 3.6°F **0.08 in./min. @ 0 ± 3.6°F
 (50 MM/MIN. @ 23 ± 2°C) (2 mm/min. @ -18 ± -3°C)

Roll Dimensions	FlexBase E 80
Width	3 ft. 3 in. (1m)
Length	34 ft. 8 in. (10.60 m)
Weight	80 lbs. (36.29 kg)
Nominal Thickness	80 mils (2,032 microns)
Net Coverage	100 sq. ft. (9.29 m ²)
Packaging	25 rolls/pallet

Eco-Facts	FlexBase E 80
Recycled Content	
Pre-Consumer	-
Post-Consumer	16%

For specific application recommendations, please contact your local Garland Representative or Garland Technical Service Department.

Installation of this product with hot oxidized asphalt may result in exposure to hazardous chemicals. Special care and attention for proper product installation must be followed in all cases. For specific details refer to the NIOSH safe handling practices in publication No. 2003-107, as well as OSHA standard 1910.134 for further exposure precautions.

ACCREDITATIONS



For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
 3800 East 91st Street
 Cleveland, OH 44105
 FAX: 216-641-0633
 Phone: 216-641-7500
 Toll Free: 800-321-9336

Garland Canada Inc.
 209 Carrier Drive
 Toronto, Ontario
 Canada, M9W 5Y8
 FAX: 416-747-1980
 Phone: 416-747-7995
 Toll Free: 800-387-5991
 (Only in Canada)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or the home office for more information.

FlexBase, Weatherking, Green-Lock and HPR are all trademarks of The Garland Company, Inc. and Garland Canada, Inc.