

HPR[®] Torch Base Sheet



OVERVIEW & FEATURES

HPR Torch Base Sheet is used as the underlayment ply for any of Garland's torch-applied membranes. It is fully compatible with both APP or SBS modified membranes. HPR Torch Base Sheet is a Styrene-Butadiene-Styrene (SBS) membrane specially formulated to accept the high heat from a torch. It has a burnable polypropylene backer that melts when the proper torching temperature has been reached. The HPR Torch Base Sheet eliminates the use of a kettle and also allows the torch applied system to be installed with a one ply underlayment.

DO NOT USE the HPR Torch Base Sheet with hot asphalt or cold adhesives.

High Tech Base Sheet - The HPR Torch Base Sheet has a high percentage of SBS rubber that when fused together with the torch-applied membrane gives the system superior puncture and abrasion resistance. It also has high tensile and elongation characteristics.

Eliminates the Use of the 2-Ply Underlayment - Because the HPR Torch Base Sheet is 120 mils (3,048 microns) thick (thicker than 2 plies of Type IV glass in hot asphalt), one ply will be sufficient as the underlayment for torch applied membrane.

Superior Strength - The HPR Torch Base membrane is reinforced with a dual fiberglass scrim. The superior strength provided by this reinforcement resists the movement created by today's modern buildings. In addition, HPR Torch Base Sheet provides tensile strength in excess of 200 pounds per inch in the machine direction. This translates to long-term resistance to splits and tears in the completed HPR torch applied roof system.

Advanced Rubber Technology - The modifier utilized in HPR Torch Base Sheet is SBS. When the SBS rubber is properly dispersed throughout the high penetration asphalt, the rubber provides increased thermal shock resistance, UV protection, heat resistance, elongation, and low temperature flexibility. To ensure proper dispersion, a special high shear mixer is used in manufacturing.

APPLICATION

The HPR Torch Base Sheet must be used for heat fusing or mechanical fastening applications only. Heat the HPR Torch Base Sheet until the burnable backer is melted. As this occurs, the SBS coating becomes tacky and is ready to roll in place.

HPR® Torch Base Sheet

Technical Data	HPR Torch Base Sheet
Tensile Strength	MD 210 lbf./in. (36.75 kN/m) XD 210 lbf./in. (36.75 kN/m)
Tear Strength	MD 300 lbf. (1334 N) XD 300 lbf. (1334 N)
Elongation	MD 6.0% XD 6.0%
Low Temperature Flex	-30°F (-34°C)


Finished membrane meets and/or exceeds ASTM D 6163, TYPE III
Test Method ASTM D 5147 is tested at:
2 in./min. @ 73.4 ± 3.6°F
(50 MM/MIN. @ 23 ± 2°C)

Roll Dimensions	HPR Torch Base Sheet
Width	3 ft. 3 in. (1m)
Length	34 ft. 8 in. (10.60 m)
Weight	76 lbs. (34.47 kg)
Nominal Thickness	120 mils (3,048 microns)
Net Coverage	100 sq. ft. (9.29 m²)
Packaging	25 rolls/pallet

Eco-Facts	HPR Torch Base Sheet
Recycled Content	
Pre-Consumer	—
Post-Consumer	6%

For specific application recommendations, please contact your local Garland Representative or Garland Technical Service Department.

Installation of this product with hot oxidized asphalt may result in exposure to hazardous chemicals. Special care and attention for proper product installation must be followed in all cases. For specific details refer to the NIOSH safe handling practices in publication No. 2003-107, as well as OSHA standard 1910.134 for further exposure precautions.



For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
209 Carrier Drive
Toronto, Ontario
Canada, M9W 5Y8
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

The Garland Company UK LTD
Second Way Centre, Second Way
Avonmouth, Bristol UK BS11 8DF
Phone: 011 44 1174 401050 (Outside UK)
Toll Free: 0800 328 5560 (Only in UK)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or the home office for more information.

HPR is a trademark of The Garland Company, Inc., Garland Canada Inc. and The Garland Company UK, LTD.

© 2017 Garland Industries, Inc.

HPR TB 0421