

# CPR™ Seam Sealers

CPR Seam Sealer BG • CPR Seam Sealer TG



## OVERVIEW & FEATURES

CPR Seam Sealer is a synthetic liquid rubber, brush grade (BG) or trowel grade (TG) mastic that was specifically designed for application to metal roofs, walls, and problem areas such as gutters, expansion joints, etc. CPR Seam Sealer can be easily applied over sloped, contoured surfaces and will provide long lasting protection. It cures to a monolithic rubbery membrane with high tensile strength and the ability to elongate and recover.

For areas that experience high movement, use either CPR Seam Sealer in combination with Grip Polyester™ Soft for long lasting protection.

**Durable** - CPR Seam Sealer has exceptional resistance to UV damage and deterioration due to weathering.

**Versatile** - CPR Seam Sealer can contour to irregular shapes and surfaces.

**Stable & Resilient** - The CPR system forms a rubber-like monolithic membrane over the entire surface. It is elastic regardless of the temperature and will expand and contract with the movement of the substrate.

**Contractor Friendly** - The CPR Seam Sealers are formulated for easy application allowing these products to conform better to irregular surfaces greatly reducing the application time for the contractor.

## SURFACE PREPARATION

All surfaces to be coated must be clean, dry and free from dust, dirt and all foreign matter. The substrate must be moisture free. On previously coated surfaces, the old coating must have firm adhesion to the substrate and be unaffected by the new coating. Unless these conditions are met, the old coating must be removed. Tests should also be done on a bleed through as in the case of bituminous roofing.

## APPLICATION

**CPR Seam Sealer BG** - All cracks and seams more than 1/64" wide and less than 1/8" wide must be filled and sealed with CPR Seam Sealer BG.

Apply at a minimum of 0.67 gal/100 sq. ft. in one coat to provide full protection to the surface.

For long-lasting protection, Grip Polyester Soft can be incorporated with the coating or when applicable may be utilized as a reinforcement and underlayment to the CPR Seam Sealer BG. CPR Seam Sealer BG may be applied with a paint brush or heavy nap roller. The coating should be allowed to dry 24 hours before applying the CPR Base Coat.

**CPR Seam Sealer TG** - Openings and joints wider than 1/8" wide should be covered with Grip Polyester Soft before using CPR Seam Sealer TG.

Apply at 1 gal./14 ln. ft. at 8" wide pass at 1/4" thick.

CPR Seam Sealer TG is typically applied by trowel or caulking gun. It is applied as easy as any plastic cement, but cures after application to provide a monolithic rubber-like seal.

## PRECAUTIONS

- Do not apply when the ambient temperature is below 40°F (5°C) or above 95°F (35°C)
- Do not apply when the surface temperature is above 140°F (60°C)
- Do not use on roof areas subject to ponding water
- Do not apply when rain is expected within 12 hours
- Do not allow the product to freeze
- Store material in dry protected areas and on a clean, raised platform
- Do not apply over silicone coatings

# CPR Seam Sealers

Technical Data	CPR Seam Sealer BG	CPR Seam Sealer TG
<b>Flash Point</b> (ASTM D 93)	105°F (40.6°C)	105°F (40.6°C)
<b>Viscosity</b> (ASTM D 2196)	140 KU	400,000-600,000 cP
<b>Non-Volatile</b> (ASTM D 1644)	75%	60%
<b>Density @ 77°F (25°C)</b> (ASTM D 1475)	9.12 lbs./gal. (1.09 kg/L)	8.9 lbs./gal. (1.06 kg/L)
<b>Dry Time @ 70° F (21.1°C)/50% RH To Touch Throughout</b>	2-3 hours 3 days	24 hours 4 days
<b>Elongation</b> (ASTM D 412)	200% min.	400% min.
<b>Tensile Strength</b> (ASTM D 412)	200 psi	600 psi
<b>Water Vapor Permeability</b> (ASTM E 96)	0.2 perms	0.15 perms
<b>Shelf Life</b>	12 months	12 months
<b>Coverage</b>	0.67 gal./sq. (0.27 l/m <sup>2</sup> )	1 gal./14 ln. ft. @ 8" wide x 1/4" thick
<b>Color</b>	Gray	Gray
<b>Packaging</b>	5 gallon pail (18.9 L)	5 gallon pail (18.9 L)

Eco-Facts	BG	TG
<b>VOC</b>	<420 g/L	<300 g/L

For specific application recommendations, please contact your local Garland Representative or Garland Technical Service Department.

Please refer to the product information, Material Safety Data Sheet, and labeling for the potential risks and benefits. Exposure to this product may cause skin and respiratory tract irritation; prolonged skin exposure may result in skin cancer; inhalation of vapors may cause central nervous system effects and long term exposure has been associated with kidney, bladder, scrotum and lung cancer.



For more information, visit us at: [www.garlandco.com](http://www.garlandco.com)

**The Garland Company, Inc.**  
3800 East 91st Street  
Cleveland, OH 44105  
FAX: 216-641-0633  
Phone: 216-641-7500  
Toll Free: 800-321-9336

**Garland Canada Inc.**  
209 Carrier Drive  
Toronto, Ontario  
Canada, M9W 5Y8  
FAX: 416-747-1980  
Phone: 416-747-7995  
Toll Free: 800-387-5991  
(Only in Canada)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. A ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or Garland Corporate Office for more information.

CPR and Grip Polyester are trademarks of The Garland Company, Inc.

©2024 Garland Industries, Inc.

CPR SS BG 0624