



OVERVIEW & FEATURES

R-Mer Coat is a premier industrial maintenance coating utilizing Kynar Aquatec® PVDF resin to restore weathered coated metal surfaces. Its fluoropolymer composition ensures superior color and gloss retention and offers greater resistance to UV degradation than conventional acrylic paints. R-Mer Coat not only protects building facades but also provides a striking finish that enhances aesthetic appeal. Used as a system with its specialized primer, R-Mer Coat transforms worn coated metal surfaces, including roofing and wall panels, into durable, vibrant structures.

Unparalleled Weathering Resistance – Unlike traditional exterior acrylic or urethane systems, R-Mer Coat's unique Kynar Aquatec PVDF chemistry prevents fading, chalking, and dirt pick-up with unprecedented UV-resistance, increasing the service life of metal building exteriors such as roofing, decorative features, support structures, wall panels or edge metal.

Reduced Maintenance Costs – R-Mer Coat's exceptional weather resistance significantly reduces maintenance expenses by eliminating the need for re-coating for years after installation, even with dark or vibrant colors.

Tenacious Adhesion – R-Mer Coat's specialized primers are formulated to help the system adhere effectively to a wide range of coated metal substrates. This includes surfaces that are typically difficult to coat, such as factory-applied Kynar 500 finishes.

Expansive Color Selection – R-Mer Coat is available in all colors offered through Garland's Metal Color Chart, but is also capable of being color-matched to any color the customer desires. The minimum order quantity for custom color-matching is 25 gallons.

APPLICATION

The service life of the coating system is directly related to the surface preparation. The surface to be coated must be properly prepared, repaired, dry, clean and free of all contamination. Preparation varies with the substrate to be coated. For roof slopes greater than 3:12, R-Mer Coat may need to be applied in multiple coating layers to meet required coverage rates. Consult your Garland Technical Department for specific prep recommendations and which R-Mer Coat primer is required. R-Mer Coat must be applied with approved spray equipment—the Graco GMAXII 7900 or an equivalent pump. The airless spray pump must have a minimum 2,000 psi output pressure rating as well as adequate delivery volume to support the spray tip orifice gallons per minute rating. Please consult the Garland R-Mer Coat spray guide for complete details.

Ambient air temperature at the time of application is important to the coating performance. Be sure to check that the air, surface and material temperature are between 50°-90°F (10°-32.2°C) and at least six Fahrenheit degrees (three Celsius degrees) above the dew point and rising. Do not apply if rain is expected within 24 hours or if the air or surface temperature is expected to drop below 50°F (10°C) for 24 hours after application. Do not apply the coating in direct sunlight as the flow and cure time can be negatively affected.

Agitate R-Mer Coat with a mixer for 2-3 minutes, then spray apply the topcoat to the primed surface at a wet film build of 5-6 mils, which will provide a coverage rate of 350-400 sq. ft. per gallon (8.6-9.8 m²/l) under normal weather conditions described above. Allow 6 hours of cure time prior to applying the second installation of R-Mer Coat at the same coverage rate.

At 77°F (25°C) and 50% humidity, R-Mer Coat will dry to the touch in 30-60 minutes. It will be dry enough to re-coat in 6 hours. The coating will fully cure in 30 days.

NOTE: Coverage rates will vary depending on your surface profile.

CLEAN-UP

Use warm soapy water to thoroughly clean application equipment and to remove wet paint. Any cured or dried coating will have to be removed with standard grade paint thinner. After cleaning, flush spray equipment with water or a water/solvent blend.

PRECAUTIONS

- Includes a stretch factor of 15-30% when calculating metal roof surface area to ensure enough coating is ordered.
- Do not apply when the ambient temperature is below 50°F (10°C) or above 90°F (32.2°C).
- Do not apply to metal substrates where the surface temperature is above 140°F (60°C).
- Do not attempt to apply this product by brush or roller, it must be sprayed.
- Do not allow this material to freeze.
- Consult the product SDS before attempting to apply.
- Cured R-Mer Coat is slippery when wet, be cautious when walking on roof.
- Coverage rates may vary based on surface condition/ texture and do not take into account material loss due to spraying, surface texture, surface absorption, waste, etc.



Technical Data	R-Mer Coat
Density @77°F (25°C) ASTM D1475	9-12 lbs/gal (1.08-1.44 g/ml) <i>Varies depending on the color</i>
Type	Water Based
Clean-Up	Warm, Soapy Water
Viscosity ASTM D2196	70-90 KU @77°F (25°C)
Solids % by weight	39-55% <i>Varies depending on the color</i>
Solids % by volume	35-45% <i>Varies depending on the color</i>
Recommended Film Thickness	5-6 mil (wet), 2 mil (dry)/coat
Flash Point	>167°F (75°C)
Gloss @60°F (15.5°C)	10-20 (eggshell) 30-45 (semigloss) <i>Varies depending on the color</i>
Shelf Life	12 months, unopened container
Coverage Rate	350-400 sq.ft./gal. (8.6-9.8 m2/l) per coat (two coats required)
Packaging	5 gallon (18.92 l)

Eco Facts	R-Mer Coat
VOC	40-100 g/l (<i>depending on color</i>)
Reflectance*	
Initial	0.93
3-Year Aged	0.84
Emittance*	
Initial	0.90
3-Year Aged	0.85
SRI*	
Initial	119
3-Year Aged	105

*Bright white color

For specific application recommendations, please contact your local Garland Representative or Garland Technical Service Department.

For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
3565 Nashua Drive
Mississauga, ON L4V 1R1
Canada
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or the home office for more information.

Kynar Aquatec is a registered trademark of Arkema. R-Mer is a registered trademark of The Garland Company, Inc. and of Garland Canada Inc.