

OVERVIEW & FEATURES

Garla-Prime is a non-fibered, quick drying, asphalt based roof primer. It is formulated from specially refined asphalt and top quality penetrating oils. Garla-Prime re-saturates existing felts to form a tough, elastic bonding surface for Garland coatings. It can also be used to prime masonry surfaces and bare concrete roof decks. Garla-Prime meets and exceeds ASTM D 41.

Conditions and Restores Dry Felts - Garla-Prime's penetrating oils replace the natural asphaltic oils lost through weathering. The oils restore flexibility to the old roof surface and seal remaining dust that might still be present after standard cleaning operations.

Economical - Garla-Prime is formulated to provide maximum per gallon coverage. A gallon of Garla-Prime covers the same area as 3 - 4 gallons (11.4-15 liters) of the standard black fibered roof coating. A Garla-Prime application actually conserves finishing material by conditioning the surface and eliminating the tendency of the finishing material to soak into the dried out, existing surface.

Maximum Surface Adhesion - Garla-Prime ensures a long-lasting flexible bond between the existing roof surface and the Garland finishing material which serves as the weathercoat.

Dries Quickly, Reduces Total Job Time - Garla-Prime is formulated to dry tack-free within 30 - 40 minutes at 77°F (25°C).

APPLICATION

The roof surface should be clean and dry prior to an application of Garla-Prime. Any failed previous coating or improperly bonded material must be removed. Garla-Prime can be applied by spray, brush or roller. In cold weather, keep the material in a heated area prior to use.

Coverage rates may vary based on surface condition/texture and do not take into account material loss due to spraying, surface texture, surface absorption, waste, etc.

Technical Data	Garla-Prime
Viscosity by Zahn Cup #2 (ASTM D 4212)	18-21 sec
Flash Point (ASTM D 93)	100°F (37.7°C)
Non-Volatile (ASTM D 2369)	47.6%
Distillation (ASTM D 402)	
Volume at 370°F (188°C)	35% min.
Volume to 380°F (193°C)	55% max.
Penetration of Residue, mm/10	10-30
Softening Point of Residue	170°F to 190°F (77°C to 88°C)
Wet Film Thickness	8-16 mils
Shelf Life	12 months
Coverage	0.5-1 gal./100 sq. ft. (0.20-0.41 l/m ²)
Packaging	5 gallon pail (18.9 l)

Product meets and/or exceeds ASTM D 41, the standard specification for asphalt primer used in roofing, dampproofing, and waterproofing.

For specific recommendations and coverage rates, please contact your local Garland Representative or Garland Technical Service Department.

Eco-Facts	Garla-Prime
VOC	450 g/L

For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
3565 Nashua Drive
Mississauga, ON L4V 1R1
Canada
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. A ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or Garland Corporate Office for more information.

Garla-Prime is a trademark of The Garland Company, Inc.