

OVERVIEW

FC Primer is a two-component, fast curing, high solids epoxy primer for use on concrete surfaces.

APPLICATION

Concrete Surface Preparation - All dirt, foreign contaminants, oil, and laitance must be removed to obtain proper adhesion to the substrate. A moisture test should be performed to determine that the concrete is dry; this can be done by placing a 18" x 18" (46cm x 46cm) polyethylene sheet on the substrate and taping down the edge. If after at least 16 hours, the substrate is still dry below the sheet and no condensation is present, then the substrate is dry enough to start coating (ASTM D4263). The polyethylene sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause debonding. (See Dura-Walk 2K Application Guidelines for more information.)

Product Mixing - Side A and side B should be thoroughly agitated prior to mixing to ensure a homogeneous material. FC Primer must always be mixed with two (2) parts A and one (1) part B (part A: part B = 2:1). The combined components should be thoroughly mixed for at least three minutes.

Primer Application - Use a flat plate squeegee or heavy-duty nap roller when FC Primer is applied on concrete. If blow holes form as the primer cures, make a second pass. Allow 5-10 minutes between passes. Apply primer at a rate of 300 sf/gal (coverage rates may vary depending on surface profile). Do NOT apply to surfaces which are below 50°F (10°C) or above 110°F (43°C).

FC Primer must be completely cured prior to overcoating (approx. 2-3 hours at 75°F or 23.9°C). Do not leave primer exposed without overcoating for more than 24 hours.

STORAGE

Store product in an area so as to bring it to room temperature before using. Continuous storage should be between 60°F to 80°F (15.6°C to 26.7°C). Low temperatures or temperature fluctuations may cause crystallization and varying coverage rates.

PRECAUTIONS

- Surface temperatures must be at least 40°F (4.44°C) and rising and the ambient temperatures six Fahrenheit degrees or three Celsius degrees above the dew point and rising.
- Once mixed, use as quickly as possible. Portion out the mixed material into smaller pails to help prevent heat build up and premature curing.
- Do not proceed with application if precipitation is imminent.
- Use with adequate ventilation.
- Keep out of the reach of children.
- Refer to the SDS for more information.



Technical Data	FC Primer
Flash Point	Above 200°F (93°C)
VOC (mixed) (ASTM D 2369)	109 g/L
Solids (mixed) Weight (ASTM D 2369) Volume (ASTM D 2697)	90% 85% (mixed)
Shelf Life	12 months in unopened container
Working Time 75°F (24°C)	15-20 minutes
Color Part A Part B Combined	Clear Clear Yellow Clear Pale Yellow
Coverage	300 sf/gal
Packaging	2 parts A to 1 part B 3 - 1 gallon pails (3.7 l) 2 parts A to 1 part B 3 - 5 gallon pails (18.9 l) 2 parts A to 1 part B

For specific recommendations and coverage rates, please contact your local Garland Representative.

For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
209 Carrier Drive
Toronto, Ontario
Canada, M9W 5Y8
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or the home office for more information.

Dura-Walk is a trademark of The Garland Company, Inc.