

OVERVIEW & FEATURES

All-Sil is a one-part silicone sealant forms a durable, flexible building seal. All-Sil is intended for use in metal curtain walls, copings, panel bedding, and glazing details. All-Sil has great adhesion to PVC, many types of coated metal (including Kynar® coated), many plastics, styrofoam, and glass.

This product is a medium modulus, non-corrosive, neutral-curing, high performance sealant that cures at low humidity levels. Because of its low-modulus, high extension/compression and recovery properties, and its strong adhesion to most building materials, All-Sil performs exceptionally well under dynamic conditions accommodating long-term movement of ± 50% in properly designed joints.

APPLICATION

Surface Preparation - Joint surfaces and backer rod must be dry and free of all contaminants such as oil, grease, wax, dust, corrosion, tar, asphalt, loose aggregate, frost, form-release agents and decorative and protective coatings. Glass, metal and other nonporous surfaces must be free of any coatings and wiped clean with solvent.

Priming - Although priming is never a substitute for proper surface preparation, priming is not required on glass or anodized aluminum and usually not necessary on most other common building materials. However, plastics, paints, coatings and other treated surfaces often present difficult substrates to which to adhere. Due to the variety and unpredictable nature of these substrates, a field test is recommended to determine the adhesion of All-Sil. Because architectural stones such as marble and granite vary considerably in porosity, some bleeding of the sealant into the substrate is possible. A field test to confirm this possibility is recommended.

Joint Backing - Backer rods control the depth of the sealant and allows it to be applied under pressure. Use a size that will compress 25 percent. Open-cell polyurethane or reticulated (soft) polyethylene rod is recommended. Closed-cell polyethylene may be used but take care not to puncture the rod which can cause outgassing or bubbling/blistering in the sealant. In joints too shallow for backer rod, use a polyethylene bond-breaker tape to prevent three-sided adhesion.

Application - Joints should be masked to ensure a neat appearance. Sealant should be applied in a continuous operation using sufficient pressure to fill the joint and make complete contact to the joint sides. Tool the sealant slightly concave using mineral spirits or dry-tooling techniques. Do not tool with soap or detergent and water solutions.

Joint Design - The width of the joint should be a minimum of four (4) times the anticipated movement. The width or depth of the joint should not be less than 1/4" (6 mm). In joints up to 3/8" (9 mm) wide, the depth of the sealant should be equal to the width. In joints wider than 3/8" (9mm), but not exceeding 1-1/4" (31 mm), the depth should be maintained at 3/8" (9 mm). For joints wider than 1-1/4" (31 mm), please consult Garland's Technical Department.

Movement Capability - 50 percent extension to 50 percent compression. Joint sealants do not change volume with expansion or compression, only shape. The greater the change in shape, the greater the stress on the sealant.

Tool Time (Initial Skin) - Initial skim forms in 8-10 hours at 77°F (25°C) and 50 percent relative humidity. Higher temperatures and/or humidity will shorten this time.

Cleaning - Use mineral spirits to remove excess sealant before it cures and to clean equipment.

Storage Life - All-Sil has a shelf life of twelve (12) months from the date of shipment, when stored in original unopened cartridges at conditions not exceeding 80°F (27°C) and 50 percent relative humidity. Consistently higher temperatures and/or humidity will shorten this shelf life.

PRECAUTIONS

- Use with adequate ventilation. Avoid skin and eye contact. Skin may be cleaned with mineral spirits and then washed thoroughly with soap and water.
- May be harmful if swallowed. Do not induce vomiting. Call physician immediately. Keep away from heat and flames.
- For professional use only.
- Keep out of reach of children.
- Toxic and flammable. Use with caution and refer to solvent manufacturer's instructions and Material Safety Data Sheets

LIMITATIONS

All-Sil should not be used:

- As a cap, heel or toe bead in certain glazing installations with high-performance glass or plastic
- In joints less than 1/4" (6 mm) in depth
- In joints where contact may be made with polysulfide sealants
- In areas exposed to harsh chemicals
- On certain architectural paints and finishes without laboratory or field testing
- In horizontal joints subject to vehicular traffic unless protected by a wearing surface
- On coal tar based products; will cause discoloration

All-Sil™

Technical Data	All-Sil
Surface Temperature Range	-62°F to 400°F (-52°C to 204°C)
Tensile Strength (ASTM D 412)	190 psi
Elongation (ASTM D 412)	650%
Joint Movement Capability (ASTM C 719)	± 50
Hardness, Shore A (ASTM C 661)	15 points
Ozone/UV Resistance	Excellent
Shelf Life	18 months
Colors	Clear & Black
Packaging	10.1 oz. (300 ml) cartridge 20 oz. (600ml) sausage tube

Coverage	All-Sil
Joints Size Depth x Width	Lineal ft. (m) per 10.1 oz.
3/8 in. x 1/4 in. (.95 cm x .63 cm)	16.2 ft. (4.93 m)
3/8 in. x 1/2 in. (.95 cm x 1.27 cm)	8.0 ft. (2.43 m)
3/8 in. x 5/8 in. (.95 cm x 1.60 cm)	6.4 ft. (1.94 m)
3/8 in. x 3/4 in. (.95 cm x 1.90 cm)	5.4 ft. (1.64 m)
3/8 in. x 7/8 in. (.95 cm x 2.24 cm)	4.6 ft. (1.40 m)
3/8 in. x 1 in. (.95 cm x 2.54 cm)	4.0 ft. (1.22 m)
3/8 in. x 1 1/4 in. (.95 cm x 3.175 cm)	3.2 ft. (0.97 m)

Eco-Facts	All-Sil
VOC	40 g/l

For specific application recommendations and coverage rates, please contact your local Garland Representative or Garland Technical Service Department.

For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
209 Carrier Drive
Toronto, Ontario
Canada, M9W 5Y8
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

The Garland Company UK, LTD
Second Way Centre, Second Way
Avonmouth, Bristol UK BS11 8DF
Phone: 011 44 1174 401050 (Outside UK)
Toll Free: 0800 328 5560 (Only in UK)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. A ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or Garland Corporate Office for more information.

All-Sil is a trademark of The Garland Company, Inc. and Garland Canada, Inc.

Kynar is a registered trademark of Arkema, Inc.

© 2022 Garland Industries, Inc.

ALL-SIL 0222