

OVERVIEW & FEATURES

Revitalizer is a heavy-bodied, fiber reinforced asphalt roof maintenance coating. It is designed to seal and preserve smooth built-up roof surfaces or mineral modified bitumen roof systems and may be combined with Grip Polyester™ Firm reinforcement for added strength and durability.

Cost Effective - Revitalizer seals, waterproofs, preserves, and protects properly prepared existing smooth built-up or modified bitumen roof systems.

Easy to Apply - The cold-applied Revitalizer system eliminates the need for hot kettles and torches. This system can be applied by spray, brush or squeegee.

High Strength - When combined with Grip Polyester Firm, the Revitalizer system provides exceptional tensile strength and elongation. The system readily conforms to surface irregularities and accommodates building movement.

APPLICATION

Refer to the Revitalizer Modified Bitumen Restoration Application Guidelines for complete substrate specific repair, preparation and application requirements.

PRECAUTIONS

- Keep away from heat and open flame
- Ensure adequate ventilation
- Harmful if swallowed
- Do not thin
- Keep material warm prior to application when temperatures are at or below 60°F (15.6°C)
- Please read product SDS and Application Guide prior to use
- Product application must not be done when rain or other conditions such as fog or heavy dew are possible within a 12-hour period.
- Storage temperatures should be between 60°F to 80°F (15.6°C to 26.7°C). Indoor ventilated storage is recommended. Ensure job site storage is in a shaded and ventilated area. Do not store in direct sunlight.
- Restrict coating application when ambient temperature is greater than 95°F (35°C).
- Roof surface must be at least six Fahrenheit degrees or three Celsius degrees above the dew point and rising prior to application.
- Application should not be done when temperatures are below 40°F (4°C) or expected to drop below freezing before coating is dry

Revitalizer™

Technical Data	Revitalizer
Non-Volatile (ASTM D 4479)	Typical 69%
Density @77°F (25°C)	7.995 lbs./gal.
Viscosity @ 77°F (25°C) Stormer, round blade	16-20 sec
Asphalt Content (ASTM D 4479)	62% (by weight)
Flash Point (ASTM D 93)	105°F (41°C)
Uniformity (ASTM D 4479)	Pass
Shelf Life	12 months, unopened
Packaging	5 gal. pail (18.9 l) 55 gal. drum (208.2 l)

Eco-Facts	Revitalizer
VOC	<250 g/l

For specific application recommendations, please contact your local Garland Representative or Garland Technical Service Department.

COVERAGE RATES

Existing Surface	Final Surface	Gal./100 ft. ² w/ Grip Polyester Firm	l/m ² w/ Grip Polyester Firm
Smooth	Coated	3.0/Poly/3.0	1.2/Poly/1.2
Mineral	Coated	3.5/Poly/3.0	1.4/Poly/1.2
Smooth	Mineral	3.0/Poly/3.5	1.2/Poly/1.4
Mineral	Mineral	3.5/Poly/3.5	1.4/Poly/1.4

For more information, visit us at: www.garlandco.com

The Garland Company, Inc.
3800 East 91st Street
Cleveland, OH 44105
FAX: 216-641-0633
Phone: 216-641-7500
Toll Free: 800-321-9336

Garland Canada Inc.
209 Carrier Drive
Toronto, Ontario
Canada, M9W 5Y8
FAX: 416-747-1980
Phone: 416-747-7995
Toll Free: 800-387-5991
(Only in Canada)

Tests verified by independent laboratories. Actual roof performance specifications will vary depending on test speed and temperature. Data reflects samples randomly collected. ± 10% variation may be experienced. The above data supersedes all previously published information. Consult your local Garland Representative or the home office for more information.

Revitalizer, Grip Polyester, and Garla-Prime are trademarks of The Garland Company, Inc.